



SPECIFICATION

(Reference sheet)

• Supplier : Samsung electro-mechanics • Samsung P/N : CL02C030BO2GNNC


• Product : Multi-layer Ceramic Capacitor • Description : CAP, 3pF, 16V, ±0.1pF, C0G, 01005

A. Samsung Part Number

<u>CL</u> <u>02</u> <u>C</u> <u>030</u> <u>B</u> <u>O</u> <u>2</u> <u>G</u> <u>N</u> <u>N</u> <u>C</u> ① ② ③ ④ ⑤ ⑥ ⑦ ⑧ ⑨ ⑩ ⑪

① Series	Samsung Multi-layer Ceramic Capacitor			
② Size	01005 (inch code)	L: 0.40 ± 0.02 mm	W: 0.20 ± 0.02 mm	
③ Dielectric	COG	Inner electrode	Cu	
Capacitance	3 pF	Termination	Cu	
⑤ Capacitance	±0.1 pF	Plating	Sn 100% (Pb Free)	
tolerance		Product	Normal	
6 Rated Voltage	16 V	Special	Reserved for future use	
7 Thickness	$0.20 \pm 0.02 \text{ mm}$	① Packaging	Cardboard type, 7" reel	

B. Structure and dimension



Samsung P/N	Dimension(mm)			
(Lead Free)	L	W	Т	BW
CL02C030BO2GNNC	0.40±0.02	0.20±0.02	0.20±0.02	0.10±0.03

C. Samsung Reliablility Test and Judgement condition

	Performance	Test condition	
Capacitance	Within specified tolerance	1Mb±10% 0.5~5Vrms	
Q	460 min		
Insulation	10,000Mohm or 100Mohm⋅μF	Rated Voltage 60~120 sec.	
Resistance	Whichever is smaller		
Appearance	No abnormal exterior appearance	Microscope (×20)	
Withstanding	No dielectric breakdown or	300% of the rated voltage	
Voltage	mechanical breakdown		
Temperature	COG		
Characterisitcs	(From -55°C to 125°C, Capacitance change should be within ±30PPM/°C)		
Adhesive Strength	No peeling shall be occur on the	100g·F, for 10±1 sec.	
of Termination	terminal electrode		
Bending Strength	Capacitance change :	Bending to the limit (1mm)	
	within ±5% or ±0.5pF whichever is larger	with 1.0mm/sec.	
Solderability	More than 75% of terminal surface	SnAg3.0Cu0.5 solder	
	is to be soldered newly	245±5℃, 3±0.3sec.	
		(preheating : 80~120 ℃ for 10~30sec.)	
Decistance to	Canasitanas abangs	Coldon not 1 270 (5% 40 (40 -	
Resistance to	Capacitance change:	Solder pot : 270±5℃, 10±1sec.	
Soldering heat	within ±2.5% or ±0.25pF whichever is larger		
Vibration Test	Tan δ, IR : initial spec.	Amplitude : 4 Emm	
vibration lest	Capacitance change :	Amplitude : 1.5mm	
	within ±2.5% or ±0.25pF whichever is larger	From 10Hz to 55Hz (return : 1min.)	
Moisture	Tan δ, IR: initial spec.	2hours × 3 direction (x, y, z)	
	Capacitance change :	With rated voltage	
Resistance	within ±7.5% or ±0.75pF whichever is larger	40±2℃, 90~95%RH, 500+12/-0hrs	
	Q: 110 min		
	IR: 500Mohm or 25Mohm · μF		
Link Townserstone	Whichever is smaller	With 2000/ of the roted valters	
High Temperature	Capacitance change :	With 200% of the rated voltage	
Resistance	within ±3% or ±0.3pF whichever is larger	Max. operating temperature	
	Q: 230 min	1000+48/-0hrs	
	IR: 1,000Mohm or 50Mohm · μF Whichever is smaller		
Tompovoturo		1 avale condition	
Temperature	Capacitance change :	1 cycle condition Min. operating temperature → 25 ℃	
Cycling	within ±2.5% or ±0.25pF whichever is larger		
	Tan δ, IR : initial spec.	→ Max. operating temperature → 25°C	
		5 cycle test	
	5 cycle test		

^{*} The reliability test condition can be replaced by the corresponding accelerated test condition.

D. Recommended Soldering method:

Reflow (Reflow Peak Temperature: 260+0/-5°C, 10sec. Max)

Product specifications included in the specifications are effective as of March 1, 2013.

Please be advised that they are standard product specifications for reference only.

We may change, modify or discontinue the product specifications without notice at any time.

So, you need to approve the product specifications before placing an order.

Should you have any question regarding the product specifications,

please contact our sales personnel or application engineers.

Disclaimer & Limitation of Use and Application

The products listed in this Specification sheet are **NOT** designed and manufactured for any use and applications set forth below.

Please note that any misuse of the products deviating from products specifications or information provided in this Spec sheet may cause serious property damages or personal injury.

We will **NOT** be liable for any damages resulting from any misuse of the products, specifically including using the products for high reliability applications as listed below.

If you have any questions regarding this 'Limitation of Use and Application', you should first contact our sales personnel or application engineers.

- ① Aerospace/Aviation equipment
- 2 Automotive or Transportation equipment (vehicles, trains, ships, etc)
- 3 Medical equipment
- 4 Military equipment
- ⑤ Disaster prevention/crime prevention equipment
- 6 Power plant control equipment
- Atomic energy-related equipment
- Undersea equipment
- Traffic signal equipment
- Data-processing equipment
- ## Electric heating apparatus, burning equipment
- Safety equipment
- ® Any other applications with the same as or similar complexity or reliability to the applications